



TECHNICAL DATA TABLE

PRODUCT CODE

ERC700

PRODUCT FEATURE

Shrink film

AREA OF USE

Shrink film can be used for colonization and grouping of materials.

TECHNICAL DATA

PROPERTIES	TEST METHOD	UNIT	VALUES
Thickness			40
Density	ASTMD1505	g/cm ³	0,923
Width		mm	1200-2700
Gloss	ASTMD2457	%	77
Haze	ASTMD1003	%	12
Surface Tension		Dyne/cm	38>
Tensile strength- MD	ASTMD 882-97	N/ mm	50-60
Elongation- MD	ASTMD 882-97	%	115-125
Tensile strength- TD	ASTMD 882-97	N/ mm	65-75
Elongation- MD	ASTMD 882-97	%	350-450
COF		Non Treated Surface	0,22-0,23
Adhesion (Welding) Temperature	ASTMD1525	° C	110 °C